



Individual Rare Earth Oxide Component Disclosure – Rift Project

Supporting detail for Rare Earth Oxide (REO) values referenced in Apex Critical Minerals Corp. (“Apex” or the “Company”) news releases, corporate presentation, and website

REO (“Rare Earth Oxide”) is a reporting convention used within the rare earth industry, defined by the Company as the sum of the following individual rare earth oxides: Ce₂O₃, La₂O₃, Pr₂O₃, Nd₂O₃, Sm₂O₃, Eu₂O₃, Gd₂O₃, Tb₂O₃, Dy₂O₃, Ho₂O₃, Er₂O₃, Tm₂O₃, Yb₂O₃, Lu₂O₃, and Y₂O₃. NdPr distribution is calculated as (Nd₂O₃ + Pr₂O₃) / REO × 100.

REO is not a directly measured assay result. Individual rare earth elements are reported by the analytical laboratory in parts per million (ppm) on an elemental basis. Each element is converted to its corresponding oxide using a fixed gravimetric conversion factor derived from molecular weight ratios, as set out in Table 1 below. The oxide value for each element is calculated as:

$$\text{Oxide (ppm)} = \text{Element (ppm)} \times \text{Conversion Factor}$$

The REO value reported for a given sample or interval is the arithmetic sum of the fifteen individual oxide values (ppm), converted to a percentage:

$$\text{REO (\%)} = \Sigma (\text{individual oxides, ppm}) \div 10,000$$

The individual element-to-oxide conversion factors used by the Company are set out below.

Table 1: Element-to-Oxide Conversion Factors

Element	Oxide	Conversion Factor	Assay Unit
Ce	Ce ₂ O ₃	1.1713	ppm
Dy	Dy ₂ O ₃	1.1477	ppm
Er	Er ₂ O ₃	1.1435	ppm
Eu	Eu ₂ O ₃	1.1579	ppm
Gd	Gd ₂ O ₃	1.1526	ppm
Ho	Ho ₂ O ₃	1.1455	ppm
La	La ₂ O ₃	1.1728	ppm
Lu	Lu ₂ O ₃	1.1371	ppm
Nd	Nd ₂ O ₃	1.1664	ppm
Pr	Pr ₂ O ₃	1.1703	ppm
Sm	Sm ₂ O ₃	1.1596	ppm
Tb	Tb ₂ O ₃	1.1510	ppm
Tm	Tm ₂ O ₃	1.1421	ppm
Y	Y ₂ O ₃	1.2699	ppm
Yb	Yb ₂ O ₃	1.1387	ppm

Note: The conversion factors above are standard gravimetric factors based on the ratio of the molecular weight of each rare earth oxide to the atomic weight of its corresponding element, and are consistent with factors commonly applied across the rare earth exploration industry. REO values presented by the Company reflect the sum of assayed individual oxide grades and do not imply any metallurgical recovery, as recoveries have not yet been established for the Rift Project.

Table 2: Individual Rare Earth Oxide Assay Results – Rift Project

Individual oxide values (ppm) underlying all REO grades publicly disclosed by the Company to date. Shaded rows denote historical drillholes (pre-Apex).

Drillhole ID	From (m)	To (m)	Interval (m)	Ce ₂ O ₃ (ppm)	Dy ₂ O ₃ (ppm)	Er ₂ O ₃ (ppm)	Eu ₂ O ₃ (ppm)	Gd ₂ O ₃ (ppm)	Ho ₂ O ₃ (ppm)	La ₂ O ₃ (ppm)	Lu ₂ O ₃ (ppm)	Nd ₂ O ₃ (ppm)	Pr ₂ O ₃ (ppm)	Sm ₂ O ₃ (ppm)	Tb ₂ O ₃ (ppm)	Tm ₂ O ₃ (ppm)	Y ₂ O ₃ (ppm)	Yb ₂ O ₃ (ppm)	REO (%)
RIFT26-001A	177.0	319.8	142.8	6760.3	27.3	9.8	28.6	59.1	4.2	5653.8	0.8	1469.8	563.8	130.1	6.2	1.2	116.9	6.5	1.48
RIFT26-001A	248.4	319.8	71.4	8176.8	22.8	8.4	25.5	50.0	3.5	7298.2	0.7	1588.8	646.9	123.1	5.2	1.0	96.1	5.8	1.81
RIFT26-001A	248.4	301.7	53.3	8929.5	24.0	8.7	27.0	52.8	3.6	8056.9	0.8	1719.5	704.3	131.0	5.5	1.1	98.5	6.0	1.98
RIFT26-001A	248.4	293.4	45.0	9362.8	23.6	8.5	27.0	52.5	3.6	8512.6	0.7	1776.6	732.9	132.2	5.4	1.0	96.3	5.8	2.07
RIFT26-001A	248.4	282.2	33.9	9701.3	23.5	8.1	27.5	53.1	3.5	8892.8	0.7	1837.7	763.2	135.5	5.4	1.0	94.1	5.4	2.16
RIFT26-001A	248.4	273.3	24.9	10799.4	23.3	7.9	28.0	53.7	3.5	10034.6	0.6	1990.0	837.9	140.9	5.4	0.9	93.6	5.0	2.40
RIFT26-002	180.6	295.4	114.8	8366.5	36.0	12.4	39.1	78.8	5.5	6201.0	0.9	1946.1	715.8	175.8	8.2	1.4	151.0	7.5	1.77
RIFT26-002	213.8	295.4	81.6	9564.6	34.4	11.5	40.2	78.2	5.2	7097.4	0.8	2173.2	811.7	187.6	7.9	1.3	139.4	6.5	2.02
RIFT26-002	244.5	295.4	50.9	11408.2	32.3	10.6	39.7	73.5	4.9	8656.1	0.7	2442.1	951.5	191.0	7.5	1.2	125.2	6.0	2.40
RIFT26-002	277.3	295.4	18.1	13894.4	29.2	8.5	43.0	76.8	4.2	10359.7	0.6	2898.4	1166.1	211.3	7.3	0.9	98.5	4.8	2.88
RIFT26-002	279.3	291.2	11.9	14638.0	26.2	7.7	39.5	69.8	3.8	11174.2	0.5	2913.3	1201.6	199.2	6.5	0.8	90.1	4.2	3.04
RIFT26-002	327.0	337.5	10.5	6369.5	58.4	19.1	59.1	124.4	8.6	3612.9	1.3	2066.2	643.6	247.6	13.2	2.1	225.8	10.8	1.35
RIFT26-002	358.0	373.0	15.1	5373.7	77.5	31.5	65.9	139.0	12.8	3055.6	3.4	2049.2	583.6	267.7	16.0	4.1	374.8	25.3	1.21
RIFT26-002	484.9	494.9	9.9	1912.2	69.6	17.7	135.7	229.9	9.0	498.8	1.3	3183.2	505.1	671.5	18.7	1.8	238.0	9.9	0.75
RIFT26-003	177.0	301.0	124.0	8928.6	45.9	15.5	49.7	100.0	6.9	6915.7	1.2	2190.6	784.2	213.3	10.5	1.7	191.1	9.2	1.95
RIFT26-003	177.0	257.0	80.0	10472.8	49.7	17.3	55.3	111.1	7.6	8385.2	1.4	2464.1	900.6	237.8	11.4	2.0	213.8	10.8	2.29
RIFT26-003	177.0	200.7	23.7	18164.7	54.5	19.5	71.1	137.2	8.2	16008.6	1.9	3679.1	1438.1	316.5	13.3	2.4	244.9	13.9	4.02
RIFT26-003	177.0	189.5	12.5	22507.2	65.3	22.4	86.8	167.7	9.6	18526.7	2.0	4610.5	1770.0	384.1	16.3	2.7	281.9	14.7	4.85
RIFT26-003	293.0	301.0	8.0	12403.8	28.9	8.8	42.5	75.2	4.0	9631.2	0.6	2729.7	1036.4	204.1	7.3	1.0	101.7	5.1	2.63
RIFT26-003	431.5	436.4	4.9	3071.6	44.8	12.3	85.1	143.3	6.0	646.1	1.0	3095.6	649.0	436.0	11.5	1.3	163.2	7.4	0.84
RIFT26-003	478.5	483.1	4.7	1955.8	48.3	10.0	121.6	201.3	5.5	323.0	0.7	3127.9	532.6	590.9	14.9	1.0	153.9	5.2	0.71
RIFT26-003	514.7	528.1	13.5	4474.5	49.9	13.9	79.7	143.8	6.7	2016.7	1.2	2785.9	652.8	399.7	12.7	1.5	196.3	8.6	1.08
RIFT26-003	557.5	574.7	17.2	3534.7	45.8	12.3	84.7	147.9	5.9	955.4	1.0	2874.1	636.6	417.2	12.2	1.4	163.6	7.5	0.89
RIFT26-003	595.5	602.5	7.0	4263.5	28.7	6.9	67.6	113.0	3.5	1412.5	0.4	2565.5	626.9	349.7	8.3	0.7	99.2	3.7	0.96
RIFT26-003	617.6	622.2	4.6	3889.7	26.2	7.1	45.9	80.1	3.4	1482.2	0.6	1935.9	501.4	225.7	6.9	0.8	95.3	4.5	0.83
RIFT26-003	634.8	639.0	4.2	6184.4	29.4	5.8	75.6	129.4	3.3	1856.6	0.4	3413.1	912.6	389.2	9.4	0.6	90.2	3.1	1.31
RIFT26-003	663.9	668.0	4.1	4102.3	52.6	16.7	66.0	128.8	7.5	1448.3	1.4	2230.1	580.9	299.1	12.0	2.0	226.5	11.1	0.92
RIFT26-003	687.0	709.7	22.7	3556.7	22.2	5.6	53.1	90.2	2.7	1248.7	0.4	2061.6	533.7	268.0	6.7	0.6	72.8	3.3	0.79
RIFT26-003	687.0	697.9	10.9	4554.2	24.6	6.1	59.8	102.5	3.0	1762.1	0.5	2337.3	639.3	297.3	7.5	0.7	80.0	3.7	0.99
RIFT26-003	714.2	720.1	5.9	3812.0	25.2	5.5	61.6	103.8	2.9	1155.0	0.3	2418.5	598.6	313.5	7.8	0.5	74.8	2.8	0.86
RIFT26-003	751.4	762.0	10.5	3982.9	35.7	8.0	78.9	135.8	4.1	1154.8	0.8	2569.5	624.8	371.3	10.5	0.9	105.1	5.2	0.91
RIFT26-003	783.0	797.9	14.9	3141.0	52.3	15.7	65.3	125.8	7.4	1141.2	1.3	1830.6	459.4	279.0	12.4	1.7	212.4	9.6	0.74
RIFT26-003	783.0	788.5	5.5	3595.1	62.4	16.4	91.4	170.4	8.3	1114.5	1.4	2393.2	578.7	393.8	16.0	1.7	218.7	9.7	0.87
RIFT26-004	192.6	232.1	39.5	6620.1	31.3	10.6	32.7	65.8	4.6	4513.9	0.9	1636.3	594.0	151.1	7.1	1.2	138.3	6.8	1.38
RIFT26-004	216.5	232.1	15.6	10031.0	25.4	8.4	31.8	59.9	3.7	7598.7	0.7	2116.4	839.5	160.7	6.0	1.0	107.7	5.2	2.10
RIFT26-004	320.6	326.2	5.6	9460.3	43.9	15.2	48.3	97.0	6.4	6956.2	1.2	2245.2	789.6	218.5	10.0	1.7	182.2	9.7	2.01
RIFT26-005A	252.6	389.8	137.2	9197.8	40.5	13.8	44.1	89.5	6.0	7393.3	1.1	2099.3	788.1	194.9	9.3	1.6	170.8	8.7	2.01
RIFT26-005A	290.5	370.4	80.0	11476.1	41.3	13.6	47.4	94.9	6.0	9620.8	1.0	2466.7	955.0	212.3	9.7	1.5	169.0	8.2	2.51

Drillhole ID	From (m)	To (m)	Interval (m)	Ce ₂ O ₃ (ppm)	Dy ₂ O ₃ (ppm)	Er ₂ O ₃ (ppm)	Eu ₂ O ₃ (ppm)	Gd ₂ O ₃ (ppm)	Ho ₂ O ₃ (ppm)	La ₂ O ₃ (ppm)	Lu ₂ O ₃ (ppm)	Nd ₂ O ₃ (ppm)	Pr ₂ O ₃ (ppm)	Sm ₂ O ₃ (ppm)	Tb ₂ O ₃ (ppm)	Tm ₂ O ₃ (ppm)	Y ₂ O ₃ (ppm)	Yb ₂ O ₃ (ppm)	REO (%)
RIFT26-005A	290.5	313.5	23.1	15609.1	41.6	13.5	54.7	103.6	6.0	13919.4	1.0	3239.6	1267.2	260.4	10.1	1.5	163.8	7.7	3.47
RIFT26-005A	302.5	313.5	11.0	19665.5	42.4	14.1	56.1	105.5	6.2	18267.5	1.0	3766.7	1526.2	272.4	10.3	1.6	173.3	8.2	4.39
RIFT26-005A	418.5	426.0	7.5	7908.7	82.3	26.7	79.5	167.0	12.1	5203.2	1.9	2668.7	828.4	325.1	18.2	2.9	340.0	15.1	1.77
RIFT26-006	191.8	401.8	210.0	6106.6	31.2	10.2	32.7	69.0	4.5	4643.3	0.8	1546.7	542.2	149.4	7.2	1.2	122.3	6.4	1.33
RIFT26-006	200.2	243.3	43.2	7512.3	32.6	8.8	38.6	80.2	4.2	5399.5	0.7	2037.3	682.0	188.1	8.3	1.0	111.1	5.5	1.61
RIFT26-006	252.1	262.6	10.5	6927.0	14.2	5.3	16.2	31.2	2.2	6553.0	0.5	1273.6	508.1	84.7	3.3	0.6	57.5	3.5	1.55
RIFT26-006	258.0	262.6	4.6	10024.4	14.8	6.0	17.9	34.1	2.4	10204.4	0.5	1604.9	691.8	94.3	3.5	0.7	64.3	4.1	2.28
RIFT26-006	358.0	401.8	43.8	12650.7	35.9	11.7	44.0	84.0	5.2	10619.6	0.9	2602.9	1039.9	211.2	8.3	1.3	138.6	7.3	2.75
RIFT26-006	364.0	398.0	34.1	14055.2	32.9	10.9	42.4	78.9	4.8	12045.9	0.9	2766.3	1130.1	209.2	7.7	1.3	127.2	7.1	3.05
RIFT26-007	178.0	246.5	68.5	11268.2	24.3	8.2	31.0	59.0	3.6	10092.3	0.6	2118.9	892.3	152.4	5.9	0.9	94.6	4.9	2.48
RIFT26-008	161.7	194.0	32.3	11194.1	34.0	12.4	38.2	73.2	5.0	9747.6	1.1	2259.3	914.6	183.9	7.7	1.5	135.3	8.5	2.46
RIFT26-008	163.1	181.1	18.0	13790.1	19.4	8.0	26.2	46.4	3.0	12988.7	0.9	2351.2	1047.2	143.6	4.6	1.1	81.4	6.5	3.05
RIFT26-008	215.9	407.7	191.9	11726.8	55.2	18.8	53.6	114.7	8.3	10510.0	1.4	2387.1	935.8	219.9	12.5	2.1	229.1	11.1	2.63
RIFT26-008	231.7	283.8	52.2	15970.6	30.9	12.8	34.5	66.4	4.9	15097.7	1.3	2701.1	1190.6	171.6	7.0	1.6	139.3	9.4	3.54
RIFT26-008	245.9	283.1	37.2	17362.6	33.8	13.5	37.0	72.2	5.3	16451.1	1.3	2896.7	1281.0	181.3	7.7	1.7	150.1	9.9	3.85
RIFT26-008	307.3	319.5	12.3	24405.1	66.5	23.8	72.4	156.7	9.7	25368.7	1.5	3901.2	1718.4	298.1	16.2	2.8	273.0	13.5	5.63
RIFT26-008	372.0	402.0	30.0	16387.5	120.8	38.1	120.3	266.5	17.9	13843.0	2.4	4028.3	1403.9	459.5	27.8	4.1	502.8	20.6	3.72
RIFT26-009	235.8	287.0	51.2	7471.9	40.9	12.9	42.7	87.3	5.8	5876.6	0.9	1883.4	665.8	187.6	9.1	1.4	162.1	7.4	1.65
RIFT26-009	235.8	258.0	22.2	10987.2	38.9	11.2	45.7	91.3	5.4	9480.9	0.7	2422.6	907.0	212.0	9.1	1.1	146.1	5.7	2.44
RIFT26-009	427.7	432.9	5.2	7861.4	38.6	11.9	44.5	86.8	5.4	4828.6	0.9	2417.9	810.7	215.5	8.6	1.2	153.7	6.8	1.65
RIFT26-010	166.3	406.0	239.7	7449.7	43.1	14.8	43.8	90.5	6.5	5717.2	1.1	1842.2	644.6	184.1	9.7	1.7	175.8	9.0	1.62
RIFT26-010	166.3	238.8	72.6	9180.2	42.7	14.5	45.3	90.8	6.4	7532.7	0.9	2198.9	785.4	205.9	9.6	1.6	173.7	8.0	2.03
RIFT26-010	166.3	216.8	50.6	10654.9	40.1	13.7	44.2	87.6	6.0	9206.1	0.9	2367.1	880.0	208.0	9.2	1.5	162.7	7.9	2.37
RIFT26-010	166.3	196.5	30.2	13827.7	42.5	14.3	49.3	97.0	6.4	12252.8	1.0	2922.7	1114.9	240.8	10.0	1.6	168.6	8.4	3.08
RIFT26-010	334.9	343.0	8.1	14497.0	49.3	17.5	49.8	105.3	7.4	12796.4	1.5	2754.7	1122.4	211.6	11.6	2.0	202.4	11.8	3.18
RIFT26-010	391.1	406.0	14.9	22910.5	129.3	40.5	145.2	308.4	18.5	19068.1	2.7	5327.6	1832.3	577.1	30.6	4.4	510.8	22.3	5.09
RIFT26-012	174.2	325.5	151.4	11000.8	41.6	13.8	46.5	93.6	6.1	9272.5	1.1	2426.1	911.9	212.1	9.6	1.6	162.5	8.5	2.42
RIFT26-012	211.3	281.0	69.7	13347.7	35.6	11.3	44.0	86.3	5.0	11595.7	0.9	2702.4	1060.3	212.0	8.6	1.3	134.3	7.0	2.93
RIFT26-012	219.6	281.0	61.4	13769.0	34.0	10.8	42.2	82.1	4.8	12184.0	0.9	2701.8	1076.1	205.0	8.2	1.3	130.0	6.9	3.03
RIFT26-012	259.0	285.0	26.0	15393.4	22.7	7.6	31.4	58.1	3.3	14433.9	0.7	2648.5	1124.1	166.6	5.5	0.9	92.5	4.9	3.40
RIFT26-012	273.0	281.0	8.0	20200.0	21.6	7.2	32.8	59.3	3.1	19493.0	0.7	3237.2	1422.9	181.1	5.5	0.9	89.0	5.3	4.48
RIFT26-013	235.8	264.2	28.4	8484.6	36.5	11.9	48.1	90.2	5.1	5651.9	1.2	2417.9	838.0	231.3	8.8	1.5	142.6	8.8	1.80
RIFT26-014	178.6	327.1	148.5	9633.8	53.3	18.7	52.2	104.7	8.0	7438.2	1.5	2277.0	805.6	220.4	11.4	2.1	220.4	11.8	2.09
RIFT26-014	178.6	215.5	36.9	14437.0	75.6	24.3	82.7	163.5	10.7	10761.1	1.8	3635.9	1260.8	364.3	17.1	2.7	286.0	14.5	3.11
RIFT26-014	178.6	200.3	21.7	18587.7	97.1	31.3	105.2	207.5	13.8	13813.1	2.3	4662.8	1614.7	460.8	21.9	3.5	362.1	18.6	4.00
RIFT26-014	249.8	299.2	49.4	10865.1	38.8	15.2	41.3	77.7	6.2	9053.4	1.5	2169.1	828.8	180.2	8.3	1.9	178.3	11.1	2.35
RIFT26-014	255.9	280.4	24.5	12596.5	44.3	17.7	46.6	88.2	7.2	10338.8	1.8	2499.0	966.7	207.7	9.4	2.2	205.2	12.9	2.70
RIFT26-014	178.6	188.8	10.2	24416.9	128.1	41.4	140.6	275.8	18.1	18168.8	3.2	6252.4	2135.5	618.9	28.8	4.8	476.5	25.7	5.27
RIFT26-015	226.5	290.9	64.4	7168.5	48.4	15.8	51.6	106.8	7.0	4899.8	1.3	2000.7	687.4	220.9	11.0	1.8	189.2	10.0	1.54
RIFT26-015	233.3	246.0	12.7	8481.2	43.9	14.0	51.4	104.6	6.2	6352.5	1.2	2174.1	788.8	229.4	10.4	1.6	163.5	8.8	1.84
RIFT26-015	261.0	276.9	15.8	8625.4	57.3	18.9	60.4	123.8	8.2	5701.6	1.6	2412.0	823.7	260.1	12.6	2.2	225.5	12.5	1.83

Drillhole ID	From (m)	To (m)	Interval (m)	Ce ₂ O ₃ (ppm)	Dy ₂ O ₃ (ppm)	Er ₂ O ₃ (ppm)	Eu ₂ O ₃ (ppm)	Gd ₂ O ₃ (ppm)	Ho ₂ O ₃ (ppm)	La ₂ O ₃ (ppm)	Lu ₂ O ₃ (ppm)	Nd ₂ O ₃ (ppm)	Pr ₂ O ₃ (ppm)	Sm ₂ O ₃ (ppm)	Tb ₂ O ₃ (ppm)	Tm ₂ O ₃ (ppm)	Y ₂ O ₃ (ppm)	Yb ₂ O ₃ (ppm)	REO (%)
RIFT26-016	237.9	284.0	46.1	7926.2	42.8	14.8	45.3	89.2	6.2	6189.0	1.1	1964.8	715.0	199.7	9.4	1.6	162.7	8.7	1.74
RIFT26-016	255.9	283.0	27.1	9149.4	43.8	15.0	49.8	96.0	6.3	7237.4	1.1	2229.3	823.7	222.6	9.8	1.7	160.9	8.8	2.01
RIFT26-016	255.9	266.2	10.3	11434.2	36.8	12.6	44.7	83.5	5.2	9619.9	0.9	2409.0	949.2	209.9	8.4	1.4	138.9	7.1	2.50
RIFT26-017	167.7	245.0	77.3	6301.1	23.4	8.0	25.1	50.2	3.5	5252.0	0.6	1373.6	513.6	115.2	5.3	0.9	94.1	4.7	1.38
RIFT26-017	167.7	179.2	11.5	8667.1	16.5	5.4	21.8	42.5	2.4	7358.2	0.4	1643.3	648.0	109.3	4.3	0.6	65.9	3.5	1.86
RIFT26-017	232.3	245.0	12.8	8580.4	33.4	10.3	36.7	70.7	4.7	7274.7	0.6	1880.6	723.5	162.1	7.5	1.1	127.2	5.3	1.89
RIFT26-017	546.5	550.4	3.9	11458.3	21.4	6.8	43.7	69.3	2.9	8505.2	0.5	2586.9	964.5	218.3	5.6	0.8	82.9	4.4	2.40
RIFT26-018	321.9	355.7	33.7	9204.5	44.4	14.8	48.6	97.3	6.3	7276.8	1.0	2159.6	774.9	217.0	10.1	1.6	175.9	8.5	2.00
RIFT26-018	321.9	330.4	8.5	11491.1	56.6	19.0	61.8	125.2	8.3	8895.6	1.2	2695.8	984.8	272.2	13.1	2.1	223.2	10.5	2.49
RIFT26-019	321.5	519.0	197.5	9771.7	42.6	14.8	45.9	92.8	6.4	7772.7	1.2	2256.1	829.0	205.8	9.8	1.7	172.2	9.2	2.12
RIFT26-019	329.0	384.9	55.9	13233.1	40.9	15.7	45.2	88.9	6.4	11032.1	1.6	2757.8	1091.5	217.8	9.0	2.0	175.5	11.6	2.87
RIFT26-019	350.1	363.0	12.9	18128.9	30.3	12.6	36.0	66.8	4.9	16333.6	1.5	3245.8	1392.2	196.0	6.6	1.7	140.3	10.4	3.96
RIFT26-019	350.1	355.1	5.1	21141.8	30.3	12.2	39.2	71.1	4.9	18921.6	1.4	3803.5	1607.6	219.8	6.8	1.6	139.6	9.9	4.60
RIFT26-019	413.1	440.0	26.9	14282.6	30.1	9.0	41.2	79.5	4.3	12929.8	0.6	2693.9	1089.4	200.8	7.9	0.9	106.9	4.8	3.15
RIFT26-019	427.4	440.0	12.6	18749.6	41.3	12.3	58.7	113.2	5.9	16766.9	0.7	3637.6	1434.8	281.5	11.3	1.3	142.1	6.3	4.13
RIFT26-020	427.8	476.8	48.9	7422.9	22.5	6.8	30.5	59.7	3.2	5776.0	0.5	1757.6	633.1	149.8	5.7	0.7	84.7	4.1	1.60
RIFT26-020	438.8	458.3	19.5	11497.7	19.0	5.2	36.7	66.5	2.5	9215.5	0.4	2602.2	975.6	201.7	5.6	0.6	67.9	3.1	2.47
EC-043	189.0	323.1	134.1	5820.1	33.0	9.8	38.6	67.0	4.9	3671.0	0.9	1718.7	550.8	181.2	7.8	1.1	132.7	6.5	1.22
EC-043	243.8	256.0	12.2	15323.4	38.3	10.9	60.3	100.0	5.7	10914.7	0.8	3586.5	1313.7	284.3	10.2	1.2	153.7	6.8	3.18
EC-043	295.7	323.1	27.4	8857.0	35.3	10.1	54.0	77.8	5.0	5281.6	1.1	2696.5	833.3	277.9	8.6	1.4	138.3	8.5	1.83
EC-093	149.4	304.8	155.5	12210.8	33.2	12.8	45.2	60.1	5.5	10850.7	1.4	2449.2	1003.8	188.2	8.7	1.7	165.3	9.8	2.70
EC-093	179.8	234.7	54.9	14897.6	27.3	9.1	44.0	48.0	4.2	13864.5	0.9	2748.6	1202.1	180.2	8.3	1.1	117.0	6.4	3.32
NEC11-004	188.4	424.6	236.2	9673.1	45.8	15.4	44.2	119.3	7.0	7856.3	1.3	2061.6	758.1	192.9	11.0	1.7	204.5	9.5	2.10
NEC11-004	247.0	315.2	68.2	15224.4	32.6	12.9	36.1	106.6	5.2	13612.4	1.3	2673.2	1100.4	186.5	7.8	1.6	149.6	8.7	3.32

Note: Drillholes EC-043, EC-093, and NEC11-004 are historical holes drilled by prior operators, included here for completeness as they underlie previously disclosed REO values. All other holes (RIFT26-prefix) were drilled by the Company.